

# suncolor® PPE

## Technical data sheet | Revision: 05

### Description:

suncolor® PPE is an expandable EPS/PPE granulate, which can be processed into foams with increased requirements on thermal properties.

<b>Density range:</b>	25 - 150 kg/m <sup>3</sup>
<b>Granulate geometry:</b>	bead-shaped granulate
<b>Typical granulate diameter:</b>	0.6 - 1.2 mm (> 90 % by weight)
<b>Pentane content (at the time of packaging):</b>	> 4,5 % by weight
<b>Water content (at the time of packaging):</b>	< 0,3 % by weight
<b>Color:</b>	grey

### Packaging and storage:

suncolor® PPE is shipped in octabins (height max. 192 cm) on wooden pallets (114 x 114 cm) containing 1,100 kg or in corrugated metal drums containing 125 kg net of material. The octabins are not weather- or water-proof and must therefore not be exposed to outdoor conditions. In order to obtain the desired properties of suncolor® PPE, the raw material should be stored below 20 °C and be processed within one month.

### Processing:

#### > Pre-expansion:

Through the higher softening temperature, suncolor® PPE can only be expanded in dis-continuous pre-expanders. In order to achieve com-parable foam densities, higher steam pressures than for EPS are required. The minimum volumetric weight of suncolor® PPE is around 30 g/l.

Setting the desired pre-expansion density can only be performed experimentally, because it mainly depends on the pre-expander used and the steam quality.

#### > Intermediate aging:

Depending on the density, intermediate storage should be between 12 hours and 4 days.

#### > Moulding:

suncolor® PPE can be processed on commercially available moulding machines.

Compared with EPS, steaming should be increased because optimum fusion is only achieved at higher temperatures and steam pressures due to increased heat distortion temperature. Steam pressures in the range of 1.0 bar are generally recommended.

### Thermal characteristics:

The heat distortion temperature of suncolor® PPE foams has been improved by approximately 10 °C compared with EPS. The maximum operating temperature of foams made of suncolor® PPE depends on the load and the duration of the load. Contact without load of up to 104 °C is possible for a short time, 95 °C without mechanical load long time, while loads up to 20 kPa at 90 °C are possible over long periods. The thermal properties specified above, will only be achieved, when the foam has been stored for appropriate time so that the material is almost free of residual pentane.

### Shipping:

<b>ADR-Marking:</b>	Substance no. 2211 Polymeric beads, expandable
<b>Class:</b>	9
<b>Packing Group:</b>	III ADR

### Safety instructions:

Flammable pentane-air mixtures may be generated during storage and processing of suncolor® PPE. For this reason, adequate ventilation must be ensured (LEL pentane 1.3 % by volume).

The blowing agent pentane escapes relatively slowly from EPS foam blocks. Thus, when cutting recently moulded blocks, the formation of a flammable pentane-air mixture has to be anticipated. In addition, all conceivable sources of ignition must be kept away, and the build-up of electric charges has to be prevented.